



CCM All Prime – Data Sheet

Description:

CCM All Prime is a unique primer/sealer/undercoat based on a hybrid acrylic emulsion. This emulsion has outstanding adhesion to a wide variety of substrates including aged enamel paints and varnishes as well as most plastics. **All Prime** has been formulated to impart excellent gloss retention on following finish coats.

Physical Properties

Resin Type:	Hybrid Acrylic emulsion
Solvent:	Water
Colour:	White, may be tinted
Finish:	Eggshell
Drying time:	1 hours @ 18°C
Recoat time:	2 hours @ 18°C
Dry Film Thickness:	50µ minimum
No. of coats:	1 - 2
Theoretical Coverage:	6-7m ² per litre to attain 50µ DF.
Primer Needed:	None
Thinning & Cleaning:	Thin only to suit application method. Water clean up.

Performance:

- Excellent adhesion to most substrates including plastics and aged enamels and varnishes and even glass.
- Extremely fast drying and re-coat times
- Outstanding hold out for following finish coats.
- May be left for up to 12 months on exterior surfaces before applying finish coats.
- Recommended primer/undercoat for waterbased enamels.
- **All Prime** can be used under solvent enamel finishes.
- May be tinted to light and mid-tone colours.

Limitations:

- Do not apply when temperature is below or expected to fall under 10°C.
- Light sand required before application of finishing coats if left for more than 7 days.
- Test area recommended for normal hard to prime surfaces.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof.

In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.



Performance Paint Systems

Substrate Preparation:

All preparation and painting must conform to AS2311: The Painting of Buildings.

Ensure all surfaces are clean and dust free. If mould and fungus is present use **CCM House Wash**. Water blasting is the recommended method of surface preparation.

For aged varnishes and enamel paint light sanding and de-dusting is advised to ensure best adhesion.

Application:

All Prime may be applied by brush roller or spray. Thinning with water is only recommended for spray application.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof.

In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.