

NOVEPOXY HIGH BUILD FLOOR PAINT

Technical Data Sheet

Description:

CCM Novepoxy High Build Floor Paint is a 2-pack low VOC water based epoxy polyamine coating ideal for application to all forms of flooring substrates, including damp surfaces. It has high water and chemical resistance similar to its solvent counterparts, while being low VOC. Tools are able to be washed in warm soapy water.

Uses:

Ideal coating for Garage and warehouse floors, Food processing plants, Dairy units and cowsheds etc, Meat works, schools, surface that require regular steam or high pressure cleaning.

Physical Properties:

- Resin type: 2-package epoxy polyamine
 - Solvent: Water
 - Colour: Range of standard colours. Other colours available. Tint charge may apply
 - Finish: Smooth high gloss
 - Volume Solids: 55%
 - Drying Time: Touch dry 2 hours @ 20°C
 - Recoat Time: 3 – 4 hours depending on temperature & Humidity
 - Full Cure. 5 – 7 days depending on ambient temperature.
 - Pot Life: 3+ hours @ 20°C
 - Theoretical Coverage: Approximately 7-10sqm/L
 - Number of coats required: 2 coats previously painted surfaces, 3 coats unpainted concrete
 - Thinning and cleanup: Water, warm and soapy for best results
 - Abrasion Resistance: Excellent
 - Heat resistance: Alkalis – Good; Acids – Fair; Fully Cured
 - Solvent resistance: Excellent
 - Hot tyre pick-up resistance: Very good
-

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof. In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature whatsoever resulting from the use or reliance upon this

information. No representations or warranties expressed or implied or merchantability fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.

Performance and Limitations:

Ideal for application without primer to sound concrete, masonry and timber substrates; but requires an appropriate primer over metals; it is tolerant to damp surfaces, but not saturated substrates. High surface hardness with excellent resistance to abrasion and may be regularly steam cleaned or power washed when fully cured, also possesses very good resistance to hot tyre pick-up when fully cured.

Do not apply when ambient temperature is below 10°C or above a RH of 85% or when rain is likely within 6 hours. Only recommended for interior floors, as like all epoxies the surface will chalk rapidly under UV radiation. If used in an exterior environment it should be over coated with clear exterior polyurethane. For resistance to specific chemicals please consult the Technical Department of CCM.

Application:

Application by brush roller or spray is very similar to the solvent counterpart with the exception that equipment is cleaned using water. Warm soapy water is recommended for best results.

For maximum slip resistance, Anti-slip Grit may be added at the rate of 160 grams per 4 Liters of mixed Novepoxy and mixed thoroughly. It is recommended that this only be done with the first coat, the second coat being applied without aggregate to facilitate easier cleaning of the surface.

Novepoxy is supplied as a package of 3 litres of A base in a 4 litre can, with 1 litre can of hardener B. The hardener is poured into the base and mixed well. Preferably with a flat stick and not a machine stirrer as this can impart aeration. The pot life is clearly visible by the mixed paint getting very thick before it finally gels and hardens. Although the mix ratio is 3 parts A base and 1 part B hardener for best results it is best to mix full containers as supplied.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof. In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature whatsoever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.

Surface Preparation:

Concrete must be allowed to mature for at least 28 days, remove all oil, grease and other surface contaminants using an industrial detergent. Moisture content of concrete or masonry must not be above 18%, or show any signs of moisture in the plastic sheet test. Surface moisture only is not a problem.

Old dirty concrete floors must be profiled by captive blasting, and/or acid etching to provide maximum grip. Concrete surfaces containing curing compounds or seriously contaminated with oils and grease must be cleaned by captive blasting rather than acid etching.

Other surfaces must be clean and free from loose paint, and roughened by sanding etc.

Health & Safety:

Materials Safety Data Sheet MUST be consulted before using this material. If you are unsure about any aspect of using Novepoxy please consult the CCM Technical Centre on 09- 4834833.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof. In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature whatsoever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.